



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

**EP 0 864 665 A1**

(12)

**EUROPEAN PATENT APPLICATION**

published in accordance with Art. 158(3) EPC

(43) Date of publication:

16.09.1998 Bulletin 1998/38

(51) Int. Cl.<sup>6</sup>: **C23C 2/00**, **C04B 35/58**

(21) Application number: **97929561.5**

(86) International application number:  
**PCT/JP97/02364**

(22) Date of filing: **08.07.1997**

(87) International publication number:  
**WO 98/01594 (15.01.1998 Gazette 1998/02)**

(84) Designated Contracting States:

**BE CH DE DK ES FI FR GB IT LI NL SE**

(30) Priority: **08.07.1996 JP 195200/96**

(71) Applicants:

- **NIPPON STEEL HARDFACING CO., LTD.**  
Tokyo 103 (JP)
- **NIPPON STEEL CORPORATION**  
Tokyo 100 (JP)
- **HITACHI METALS, LTD.**  
Chiyoda-ku, Tokyo 100 (JP)

(72) Inventors:

- **SUHARA, Michinori**  
Nippon Steel Hardfacing Co., Ltd.  
Tokyo 103 (JP)
- **SATO, Yasunari**  
5-3, Tokai-cho Tokai-shi Aichi 476 (JP)
- **YASHIRO, Toshinori**  
Hitachi Metals, Ltd.  
Nagoya-shi Aichi 450 (JP)


(74) Representative:

**Lewin, John Harvey**  
**Elkington and Fife,**  
**Prospect House,**  
**8 Pembroke Road**  
**Sevenoaks, Kent TN13 1XR (GB)**

(54) **MECHANICAL MATERIAL DISPOSED IN HOT DIPPING BATH**

(57) By means of forming equipment for use in molten metal plating baths using a composition containing  $\text{Si}_3\text{N}_4$ : 70 - 95%,  $\text{Al}_2\text{O}_3$ : 2 - 10%,  $\text{AlN}$ : 1-10%, and  $\text{Y}_2\text{O}_3$ : 1 - 10%, it is possible to greatly extend the period of operation before the appearance of defects in the products.

FIG. 1



**EP 0 864 665 A1**

## Description

### Technical Field

The present invention relates to various types of equipment for use in baths employed in the plating of non-ferrous metals other than copper, such as, for example, molten zinc plating, molten aluminum plating, or the plating of molten zinc-aluminum alloys; in particular, the present invention relates to various types of equipment used in baths which are disposed within molten metal plating baths having a composition such that silicon nitride ( $\text{Si}_3\text{N}_4$ ) is the main component thereof (for example, bath rollers [support rollers, synch rollers, and the like], roller bearings, roller arms, melting boxes, snouts, pumps within baths, thrust locks, and the like).

### Background Art

Conventionally, materials which were resistant to melting and metal corrosion such as low carbon steel, high chromium steel, and SUS316L, and the like, were commonly employed for various types of equipment used in baths employed in molten zinc plating, molten aluminum plating, or the plating of molten zinc-aluminum alloy.

In cases requiring greater resistance to corrosion than that offered by these materials resistant to melting and metal corrosion, it is common to build up metal by welding or to form a film by flame spraying on the surfaces of these metal implements and equipment using one or a mixture of two or more of oxides, borides, nitrides, carbides, fluorides, and the like of various corrosion resistant metals such as W, Co, Mo, and Cr and the like. In this case, the outer limit of the service life during which such implements or equipment could be continuously employed without causing defects in the high grade products was within a range of 15 - 90 days.

In order to improve the productivity of the manufacturing industry, it is necessary to operate facilities over a long period of time without affecting the quality of the materials produced.

In order to respond to this need in molten metal plating operations, it is necessary that the service life, during which the implements and equipment used within the plating bath can be continuously employed, be as long as possible, in addition to management of the plating baths.

The present invention solves the problems in the conventional technology described above; it has as an object thereof to provide various types of equipment for use in molten metal plating baths which are capable of stable use over a long period of six months or more.

### Disclosure of the Invention

In order to attain the above object, the present inventors have conducted diligent research, and as a

result discovered that it is effective to form various equipment for use in molten metal plating baths using a composition having as a main component thereof silicon nitride, which is a material which does not react with the molten metal and which is easily worked; the present invention was completed based on this discovery.

The invention based on this discovery comprises equipment used in baths, such as rollers, bearings, roller arms, melting boxes, snouts, pumps, thrust locks, and the like, which are disposed within molten metal plating baths, the formation of which is conducted using a composition containing  $\text{Si}_3\text{N}_4$ : 70 - 95%,  $\text{Al}_2\text{O}_3$ : 2 - 10%,  $\text{AlN}$ : 1 - 10%,  $\text{Y}_2\text{O}_3$ : 1 - 10%, and unavoidable impurities.

### Brief Description of the Diagrams

Figure 1 is a cross-sectional view showing a molten metal plating device employing a roller in accordance with the present invention.

Figure 2 is a side view showing an embodiment of a bearing for a support roller in accordance with the present invention.

Figure 3 is a side view showing another embodiment of a bearing for a support roller in accordance with the present invention and a cross-sectional view of this bearing.

Figure 4 shows a bearing combined with the synch roller bearing part of the present invention.

### Description of the References

- 1 plating steel plate
- 2 molten metal bath
- 3 snout
- 4 synch roller
- 5 synch roller holder
- 6 support roller
- 7 support roller holder
- 8 melting box
- 9 oven
- 10 support roller cylinder
- 11 axle provided with a screw-shaped groove
- 12 axle end surface groove
- 13 projecting axle end surface
- 14 bearing
- 15 synch roller
- 16 synch roller axle
- 17 synch roller arm
- 18 synch roller bearing
- 19 synch roller thrust lock

### Best mode for carrying out the invention

The structure and function of the present invention will now be explained.

The various types of equipment for use in molten

metal plating baths having an increased service life in accordance with the present invention are formed using a composition having as a main component thereof silicon nitride, which is non-reactive with the molten metal, and which is easily worked, so that it may be industrially employed.

In order to compensate for the defects of silicon nitride, that it is deficient in shock resistance and in strength, it is commonly combined with metals; however, there are great differences in the thermal expansion coefficients of metal and ceramics, and so there has been little success in the use thereof for various types of equipment used in molten metal plating baths.

In the present invention, the formation is conducted using a solely ceramic composition having silicon nitride as the main ingredient thereof, and the design is such that sufficient shock resistance and strength are exhibited.

That is to say, in the case in which a roller support axle and a roller bearing formed with a ceramic composition having silicon nitride as the chief component thereof come into contact and rub against one another and a sufficient service life can not be obtained, a spiral groove is provided on the surface of the roller support axle, and one or more grooves are supplied on the end surface of the support axle, and by means of these grooves, molten metal enters into the gap between the surface of the roller support axle and the inner surface of the bearing, and these do not directly come into contact, so that the molten metal serves as a lubricant.

Commonly, in rotating axle bearing which employ ceramics such as metal oxides, metal carbides, metal borides, metal fluorides and the like, the ceramics are used in ball or needle form, and structures are known in which metal is used on the inner race or the outer race, or the opposite combination is employed.

There are chiefly two problems with the case described above. One of these is that although the parts formed from ceramics contribute to an increase in service life, the metal portions have the conventional short service life, and do not contribute to the increase in service life of the implements and equipment which is the object of this invention. Another drawback is that dross having an extremely high hardness, comprising an alloy of two or more metals, is in suspension in the molten metal plating bath, and this enters in between the balls or needles and the race, creating resistance and stopping the function of the bearing.

In order to avoid a stoppage in bearing function resulting from the entry of the dross, a sliding bearing has been proposed, and various such bearings have been tested or partially produced. Ceramics are affixed in some way to a portion of a bearing which is formed from metal, that is to say, to the portion of the bearing which is contact with the axle. A disadvantage in this case is in the same manner as above, the metal portions are eroded, so that the ceramic base material is eliminated, and no overall increase in service life can be

realized.

The present invention solves all the deficiencies mentioned above; herein, the bearing comprises a sliding bearing formed in a unitary manner from ceramics, and in the same way, in the case of the roller, the present invention makes possible not merely the use of ceramics at those portions which are in contact with the bearing and which experience extreme abrasion and those portions which are in contact with the steel plates and also experience extreme abrasion, but the unitary formation of the roller using ceramics. The equipment for use in molten metal plating baths of the present invention does not employ a combination of metal and ceramics, so that there is no cracking resulting from the tensile or compressive forces generated by differences in thermal expansion coefficients, and use over a long period of time is possible.

The reason for limiting the composition ranges of the ceramic component used to form the equipment for use in molten metal plating baths of the present invention will now be explained.

$\text{Si}_3\text{N}_4$ : 70 - 95%

This compound is resistant to corrosion by nonferrous molten metals other than copper, and is also resistant to acidic and alkaline conditions. Sintering formation is made possible by adding small amounts of  $\text{Al}_2\text{O}_3$ ,  $\text{Y}_2\text{O}_3$ , and the like. At amounts of less than 70%, the thermal resistance and resistance to corrosion are insufficient, while when the amount is in excess of 95%, sintering formation becomes impossible.

$\text{Al}_2\text{O}_3$ : 2 - 10%  $\text{Y}_2\text{O}_3$ : 1 - 10%

By adding both of these together, the sintering formation of the  $\text{Si}_3\text{N}_4$  which is the chief component becomes possible. At amounts less than the lower limit, sintering becomes insufficient, while at amounts greater than the upper limit, practical application becomes impossible as a result of the decline in thermal resistance and resistance to corrosion.

$\text{AlN}$ : 1 - 10%

This compound has a high thermal conductivity and a high hardness, and serves to increase the strength. At amounts of less than 1%, these effects can not be realized, while amounts of more than 10%, the brittleness increases, and shock resistance declines.

When substances or elements other than these four are included as unavoidable impurities, the effects of the present invention will be undisturbed if the total amount is less than 1%.

An embodiment of the present invention will now be discussed; however, the present invention is not limited to this embodiment.



## Embodiment 1

87%  $\text{Si}_3\text{N}_4$ , 3%  $\text{AlN}$ , 5%  $\text{Al}_2\text{O}_3$ , and 5%  $\text{Y}_2\text{O}_3$  by weight were mixed in powdered form (having a grain size of 1.2 micrometers), 0.5 parts per weight of polyvinyl butyral were added as a binder to 100 parts per weight of the raw material powder, and this was agitated to produce a mixture, this mixture was then press-formed at a pressure of  $1,000 \text{ kg/cm}^2$ , and this was sintered for a period of 5 hours in a nitrogen atmosphere at a temperature of  $1750^\circ\text{C}$ , and the roller (having a diameter of 250 mm, a length of 1,900 mm, an axle diameter of 90 mm, an axle length of 150 mm, and an axle screw depth of 2 mm, and a pitch of 26 mm) and the bearing (having an inner diameter of 93 mm, an outer diameter of 140 mm, and a length of 120 mm) shown in figure 3 were obtained. The characteristics of the ceramic roller and bearing after sintering are as shown below.

Flexural strength  $100 \text{ kg/mm}^2$

Surface hardness HV 1,580

Resistance to corrosion (test solution: test piece test using a molten zinc bath) Erosion loss: 1 mg/month or less

Resistance to abrasion (test conditions: an installed support roller bearing) Amount of abrasion: 4 g/month or less

The roller and bearing obtained in embodiment 1 were incorporated into the plating device of Figure 1 (a molten zinc bath having a temperature of  $470^\circ\text{C}$ ), and this was operated continuously for a period of one month with respect to cold rolled steel plates (type of steel: low carbon aluminum killed steel, physical properties:  $\text{Yp } 28 \text{ kgf/mm}^2$ ,  $\text{Ts } 36 \text{ kgf/mm}^2$ ) having an average width of 1,200 mm and an average thickness of 1.25 mm at an average pass through speed of 115 m/min, and after maintenance, the roller of the present invention was used six times under the same conditions, and no defects were produced in the surface of the roller.

For the purposes of comparison, hard chromium plating having a thickness of 30 micrometers was executed on a roller axle and bearing comprising SUS316L having the same size as that of embodiment 1, and this was subjected to plating operations under the same conditions. It was necessary to change the roller after a period of ten days from the initiation of operations because of the rough quality of the roller surface.

As described above, the equipment of the present invention exhibits an extremely long service life in the case of rollers, roller bearings, and thrust locks which are subjected to abrasion and rubbing; those portions which do not experience rubbing and abrasion, such as roller arms, melting boxes, and snouts have a semi-permanent service life. When conventional technologies are applied to such equipment, the surface life thereof is 2 - 3 years, with the exception of the oven.

## Industrial Applicability

The present invention is structured as described above, so that equipment for use in molten metal plating baths having an extremely long service life is obtained, and it is possible to greatly extend the period of continuous operation during which no equipment is replaced, and this is extremely useful in industry.

## Claims

1. Equipment for use in baths which is disposed within molten metal plating baths, having a composition containing  $\text{Si}_3\text{N}_4$ : 70 - 95%,  $\text{Al}_2\text{O}_3$ : 2 - 10%,  $\text{AlN}$ : 1 - 10%,  $\text{Y}_2\text{O}_3$ : 1 - 10%, and unavoidable impurities.
2. Equipment for use in baths which is disposed within molten metal plating baths in accordance with claim 1, wherein said equipment used in molten metal plating baths is a roller used in such baths, and a screw shaped groove is formed on a surface of a support axle of said roller, and one or more grooves are formed on an end surface of said support axle.
3. Equipment for use in baths which is disposed within molten metal plating baths in accordance with claim 1, wherein said equipment used in molten metal plating baths comprises rollers used in such baths, a screw shaped groove is provided on the surface of a support axle of said roller, and an end surface of said support axle is formed in a protruding manner.
4. Equipment for use in baths which is disposed within molten metal plating baths in accordance with claim 1, wherein said equipment used in molten metal plating baths comprises a bearing for rollers used in such baths, and said bearing has a square concave shape in lateral cross section.
5. Equipment for use in baths which is disposed within molten metal plating baths in accordance with claim 1, wherein said equipment used in molten metal plating baths comprises a bearing for rollers in such baths, and said bearing has a cylindrical shape.

FIG. 1




FIG. 2




FIG. 3





FIG. 4



## INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP97/02364

## A. CLASSIFICATION OF SUBJECT MATTER

Int. Cl<sup>6</sup> C23C2/00, C04B35/58

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

Int. Cl<sup>6</sup> C23C2/00-2/40, C04B35/58

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Jitsuyo Shinan Koho	1926 - 1997
Kokai Jitsuyo Shinan Koho	1971 - 1997
Toroku Jitsuyo Shinan Koho	1994 - 1997

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP, 1-159359, A (Sumitomo Metal Industries, Ltd.), June 22, 1989 (22. 06. 89) (Family: none)	1 - 5
A	JP, 61-37955, A (Osaka Fuji Kogyo K.K.), February 22, 1986 (22. 02. 86) (Family: none)	1 - 5
A	JP, 6-322457, A (Hitachi Metals, Ltd.), November 22, 1994 (22. 11. 94) (Family: none)	1 - 5
A	JP, 59-182276, A (Toshiba Corp.), October 17, 1984 (17. 10. 84) & EP, 124989, A1	1 - 5

☐ Further documents are listed in the continuation of Box C.☐ See patent family annex.

## \* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&amp;" document member of the same patent family

Date of the actual completion of the international search

September 30, 1997 (30. 09. 97)

Date of mailing of the international search report

October 14, 1997 (14. 10. 97)

Name and mailing address of the ISA/

Japanese Patent Office

Facsimile No.

Authorized officer

Telephone No.

Form PCT/ISA/210 (second sheet) (July 1992)